

MARIPOL DCO - 40 SEMI DRYING ALKYD SHORT OIL

➤ **General Description**

Short oil alkyd resin for stoving finishes in combination with amino resin, as polymeric plasticizer with nitrocellulose lacquers for air drying acid cured wood finishes.

➤ **Other Characteristics**

- OIL : Dehydrated castor oil
- OIL LENGTH : Approx. 40%
- POLYOL : Glycerin
- % NON VOLATILE : 70 ± 1%
- SOLVENT : Xylene
- ACID VALUE : 10 - 15 mgm of KOH/gm of solid resin
- VISCOSITY AT 30°C : PRA tube no. 9 – 10
or 4-8 poises or
120-170 secs. By ford cup no. 4
- COLOUR : 5 (on gardner disc.)
(70% SOLUTION)

➤ **Disclaimer**

The information contained within this data sheet is based on information believed to be reliable at the time of its preparation. The company will not be liable for loss or damage howsoever caused including liability for negligence which may be suffered by the user of the data contained herein. It is the users' responsibility to conduct all necessary tests to confirm the suitability of any product or system for their intended use. No guarantee of results is implied since conditions of use are beyond our control.