

MARIPOL L-60 OXIDISING LONG OIL ALKYD RESIN

➤ **General Description**

BFRLO based long oil alkyd.

➤ **Areas of application**

Excellent quality synthetic enamels having very good flow, gloss retention, fast drying and good hardness.

➤ **Other Characteristics**

- OIL : BFRLO
- OIL LENGTH : Approx. 60%
- POLYOL : Pentaerythritol
- % NON VOLATILE : $60 \pm 1\%$
- SOLVENT : Mineral Turpentine
- ACID VALUE : Below 12 mgm of KOH/gm of solid resin
- VISCOSITY AT 30°C : 100 ± 20 Secs. in 50% M.T.O
by Ford Cup No.4
- COLOUR : 4 (on Lovibond Scale)

➤ **Disclaimer**

The information contained within this data sheet is based on information believed to be reliable at the time of its preparation. The company will not be liable for loss or damage howsoever caused including liability for negligence which may be suffered by the user of the data contained herein. It is the users' responsibility to conduct all necessary tests to confirm the suitability of any product or system for their intended use. No guarantee of results is implied since conditions of use are beyond our control.