

MARIPOL M-2595 / MARIPOL TTM-45 SEMI DRYING MEDIUM OIL ALKYD RESIN

➤ **General Description**

Soya oil/ Fatty acid based medium oil alkyd resin with reasonable gloss and drying properties

➤ **Area of application**

Economical industrial enamels and primers.

➤ **Other Characteristics**

- OIL : Refined Soyabean Oil / Soyabean Fatty Acid.
- OIL LENGTH : Approx. 48%
- POLYOL : Pentaerythritol
- % NON VOLATILE : $50 \pm 1\%$
- SOLVENT : Mineral Turpentine
- ACID VALUE : Below 15 mgm of KOH/gm of solid resin
- VISCOSITY AT 30OC : 180 ± 20 secs. in 40% M.T.O. by Ford Cup No.4
- COLOUR : 3 (on Lovibond Scale)

➤ **Disclaimer**

The information contained within this data sheet is based on information believed to be reliable at the time of its preparation. The company will not be liable for loss or damage howsoever caused including liability for negligence which may be suffered by the user of the data contained herein. It is the users' responsibility to conduct all necessary tests to confirm the suitability of any product or system for their intended use. No guarantee of results is implied since conditions of use are beyond our control.