

## MARIPOL - RX-41 OXIDISING ROSINATED ALKYD RESIN

➤ **General Description**

Soya oil/ Fatty acid base rosinated medium oil alkyd supplied as 60% solids in Mix Xylene

➤ **Area of Application**

Industrial finishes-quick drying medium for hammer finishes.

➤ **Other Characteristics**

- OIL : Soyabean Oil
- OIL LENGTH : Approx. 32%
- POLYOL : Pentaerythritol / Glycerine
- % NON VOLATILE :  $70 \pm 1\%$
- SOLVENT : Xylene
- ACID VALUE : 15-20 mgm of KOH/gm of solid resin
- VISCOSITY AT 30°C :  $90 \pm 10$  Secs. in 50% Xylene by Ford Cup No.4
- COLOUR : 3 (On Lovibond Scale)

➤ **Disclaimer**

The information contained within this data sheet is based on information believed to be reliable at the time of its preparation. The company will not be liable for loss or damage howsoever caused including liability for negligence which may be suffered by the user of the data contained herein. It is the users' responsibility to conduct all necessary tests to confirm the suitability of any product or system for their intended use. No guarantee of results is implied since conditions of use are beyond our control.